

GALLOY & VAN ETTEN, INC.

Cut Stone and Marble Contractors

11756 S. HALSTED STREET

CHICAGO, ILLINOIS 60628-8145

PHONE (773) 928-4800

P.O. BOX 288145

FAX (773) 928-4129

May 20, 2010

To whom it may concern:

This product is not considered to be or to contain hazardous chemicals based on the evaluations made by our company under the OSHA HAZARD COMMUNICATIONS 29 CFR 1910.120.

RE: Material Safety Data Sheet

Product: A-1 invisible Stone Patcher

Manufacturer: Galloy & Van Etten, Inc.

Creation Date: July 14, 1987

Sincerely yours,



Jack Van Etten

President


MEMBER OF ALLIED STONE INDUSTRIES

FLOOD TESTING LABORATORIES, INC.

PHONE: (AREA CODE 312) 721-2200

1945 EAST 87TH STREET
CHICAGO, ILLINOIS 60617

July 14, 1987



Galloy and Van Etten, Inc.
11756 South Halsted Street
Chicago, Illinois 60628

Re: Analysis of A-1 Stone Patcher

Attention: Mr. Bernie Van Etten, Jr.

Gentlemen:

Enclosed is the analysis of your A-1 Stone Patcher. The analysis indicates the material contains no hazardous materials, and ordinary safety precautions are sufficient.

Please call if we can be of further help.

Respectfully submitted,


FLOOD TESTING LABORATORIES, INC.

Walter H. Flood, Jr.

3-
WHF:sh

FLOOD TESTING LABORATORIES, INC.

PHONE: (AREA CODE 312) 721-2200



CONSTRUCTION MATERIALS

INVESTIGATION

DESIGN AND CONTROL

CONSULTATION

RESEARCH

1945 EAST 87TH STREET
CHICAGO, ILLINOIS 60617

July 14, 1987
Page No. 1

Material Safety Data Sheet

Product: A-1 Invisible Stone Patcher
Galloy and Van Etten, Inc.

Hazardous Ingredients

<u>Material:</u>	<u>Percent:</u>
None	---

Physical Data

Appearance: Buff Colored Powder

<u>Material:</u>	<u>Percent:</u>
CaO/CaCO ₃	72
SiO ₂	11
SO ₃	13
Fe ₂ O ₃	0.5
Al ₂ O ₃	0.9
MgO	0.8
Specific Gravity:	2.83

Fire and Explosion Hazard Data

Flash Point: None
Extinguishing Media: Not Combustible
Special Procedures: None

Health Hazard Data


Effects of overexposure:

Acute: Irritating to eyes; prolonged contact with wet skin
may irritate or burn. Irritating to respiratory tract.
Chronic: Not Known.

Emergency First Aid Procedures:

Eyes: Immediately flush with water. See physician.

Skin: Wash with water and see physician if irritation persists.



July 14, 1987
Page No. 2

Material Safety Data Sheet

Product: A-1 Invisible Stone Patcher
Galloy and Van Etten, Inc.

Reactivity Data

Stability: Stable

Conditions to avoid: Moisture or high humidity

Spill or Leak Procedures

In case material is spilled:
Sweep up. Avoid dust.

Waste Disposal:
Landfill in accordance with local state and federal regulations.

Special Protection Information

Respiratory Protection: Provide general ventilation if large amounts of material are used and cause dusty conditions. Approved dust mask may be used if desired.

Protective Equipment

Gloves may be desired if using material for extended period. Protective clothing or eye protection is generally not required.

Special Precaution

Avoid water and high humidity conditions. Material will absorb water and harden.

FLOOD TESTING LABORATORIES, INC.

1945 EAST 87TH STREET
CHICAGO, ILLINOIS 60617REPORT OF TEST OF
Compressive Strength of A-1 Stone Patcher

LABORATORY NO. 870063 DATE June 3, 1987
 SAMPLED BY: Delivered April 15, 1987 AMOUNT
 SAMPLED FROM:
 MANUFACTURED BY:
 CONTRACTOR: Galloy & Van Etten, Inc.
 11756 South Halsted Street
 Chicago, Illinois 60628
 REMARKS: Attn: Mr. Bernie Van Etten

IDENTIFICATION: A-1 Stone Patcher - Buff
 2" x 2" x 2" Cubes A = 4.0 sq. in.

<u>Specimen</u>	<u>Age at Breaking</u>	<u>Compressive Strength</u>	
		<u>Lbs. Actual</u>	<u>Lbs./Sq. Inch</u>
1	1 day	5160	1290
2	7 days	8500	2125
3	28 days	11200	2800

NOTE: Water used - 29% by weight
 Cubes cured 100% humidity
 70°F

3-
 WHF:lv

RESPECTFULLY SUBMITTED:
 FLOOD TESTING LABORATORIES, INC.
 Walter H. Flood, Jr.